

Technical Data:

Pure Gum Rubber Sheet

Basic Properties	Value	Test Method	Unit
Base Polymer Type	NR	-	-
Indentation Hardness	40	ASTM D2240 00	Degrees
Specific Gravity	1.05 ± 0.5	ASTM D792	g/cm ³
Tensile Strength - Minimum	18.9	ASTM D412	Mpa
Elongation @ Break - Minimum	600	ASTM D412	%
Minimum Continuous Working Temperature	-20	-	°C
Maximum Continuous Working Temperature	85	-	°C
Maximum Intermittent Working Temperature	85	-	°C
Compression Set 70 Degrees 22 Hours	Not Available	-	%
Insertion Type	N/A	-	-

Guidelines for Use

Food Use Suitability	Not Recommended
Abrasion Resistance	Excellent
Ozone Weather Resistance	Not Recommended
Flame Retardancy	Not Recommended
Electrical Resistance	Not Recommended
General Purpose	Not Recommended

The specifications for all products are based on the provided mix test results and represent key statistical product figures, but do not specifically guarantee properties. The right to changes for the purpose of technical advancement that do not substantially modify the product are reserved.